

(51) International Patent Classification <sup>7</sup> : B24B 37/04, B24D 13/14, 13/12, B29C 35/08		A1	(11) International Publication Number: WO 00/34008
			(43) International Publication Date: 15 June 2000 (15.06.00)
(21) International Application Number: PCT/US99/28190		(81) Designated States: JP, KR, SG, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 29 November 1999 (29.11.99)			
(30) Priority Data: 09/207,793 9 December 1998 (09.12.98) US		Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(71) Applicant: APPLIED MATERIALS, INC. [US/US]; 3050 Bowers Avenue, Santa Clara, CA 95052 (US).			
(72) Inventor: TOLLES, Robert, D.; 2375 Amethyst Drive, Santa Clara, CA 95051 (US).			
(74) Agents: BERNADICOU, Michael, A. et al.; Blakely, Sokoloff, Taylor & Zafman LLP, 7th floor, 12400 Wilshire Boulevard, Los Angeles, CA 90025 (US).			

A cross-sectional view of a multi-layered structure 100. The structure consists of several layers: a top layer 102, a middle layer 104, and a bottom layer 106. A central layer 107 is also indicated. The layers are separated by interfaces 108. The structure is shown with diagonal hatching for the layers and a central horizontal line for the interface.

A method for selectively altering a polishing pad (100) adhesive layer (106) includes providing a mask (120) having transparent regions (124) and opaque regions (122) and directing radiation toward the mask (120) so that the radiation passes through the transparent regions (124) and impinges onto the adhesive layer (106) on the polishing pad (100). The area of the adhesive layer corresponding to the transparent regions (124) of the mask (120) is cured to be less adhesive. The area of the adhesive layer corresponding to the opaque regions (122) remain adhesive.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

A POLISHING PAD WITH A PARTIAL ADHESIVE COATINGBackground

The invention relates to chemical mechanical polishing of substrates, and more particularly to a polishing pad with a partial adhesive coating, and to methods and apparatus for producing such polishing  
5 pads.

Integrated circuits are typically formed on substrates, particularly silicon wafers, by the sequential deposition of conductive, semiconductive or insulative layers. After each layer is deposited, the  
10 layer is etched to create circuitry features. As a series of layers are sequentially deposited and etched, the outer or uppermost surface of the substrate, i.e., the exposed surface of the substrate, becomes successively more non-planar. If the outer  
15 surface is non-planar, then photolithographic techniques to pattern photoresist layers might not be suitable, as a non-planar surface can prevent proper focusing of the photolithography apparatus. Therefore, there is a need to periodically planarize  
20 this substrate surface to provide a planar layer surface.

Chemical mechanical polishing is one accepted method of planarization. This planarization method typically requires that the substrate be mounted on a carrier or  
25 polishing head, with the surface of the substrate to be polished exposed. The substrate is then placed against a rotating polishing pad. In addition, the carrier head may rotate to provide additional motion

- 2 -

between the substrate and polishing surface. Further, a polishing slurry, including an abrasive and at least one chemically-reactive agent, may be spread on the polishing pad to provide an abrasive chemical solution at the interface between the pad and substrate.

A typical polishing pad includes a hard top layer and a softer bottom layer. The top layer has a high friction polishing surface, capable of transporting slurry, and a second surface adhesively bonded to a first surface of the bottom layer. A second surface of the bottom layer is typically attached to a platen by a high strength pressure-sensitive adhesive layer.

One consideration in the production of integrated circuits is process and product stability. To achieve a low defect rate, each substrate should be polished under similar conditions, i.e., same polishing surface structure. A limitation on process stability, as well as polishing throughput, is "glazing" of the polishing pad. "Glazing" occurs when the polishing pad is frictionally heated and compressed in regions where the substrate is pressed against it, as well as worn as a result of the abrasive contact. The peaks of the polishing pad are pressed and worn down and the pits of the polishing pad are filled up, so the surface of the polishing pad becomes smoother and less abrasive. As a result, the polishing time required to polish a substrate increases. Therefore, the polishing pad surface must be periodically returned to a more uniform abrasive condition, with higher friction and ability to transport slurry. This process is defined as "conditioning" and serves the purpose of

- 3 -

maintaining a high polishing rate. The conditioning process can be destructive for the polishing pad and results in reducing the lifetime of the polishing pad. Because of these reasons the polishing pad needs to be removed from the platen and replaced every 100 to 1000 substrates, depending upon the type of substrate and conditioning process.

In order to remove the pad, an operator reaches into the polishing area, grasps the polishing pad by hand or with mechanical aids and pulls it to peel it off the platen. Because of the high strength of the adhesive layer, the operator must apply a large force to pull the polishing pad off the platen. For example, the operator may need to apply pulling force of approximately 100 pounds. This large force can exceed the physical abilities of the operator and can pose a risk of injury.

#### Summary

In general, in one aspect, the invention features a polishing pad including a first layer having a polishing surface, and a second layer having an adhesive region and a cured region disposed on a surface of the first layer opposite the polishing surface.

Implementations of the invention may include one or more of the following features. The polishing pad may have a plurality of adhesive and cured regions. The cured regions may be partially or entirely cured. The cured regions may be circles or arc segments arranged in a pattern. The cured region and the adhesive region may form concentric circles. A third layer may

- 4 -

be disposed between the first and second layers opposite the polishing surface.

5 In general, in another aspect, the invention features an apparatus for selectively altering a polishing pad adhesive layer. The apparatus includes a radiation source generating a radiation beam, a support for the polishing pad, and a mask having a transparent region and an opaque region. The mask is disposed between the radiation source and the substrate holder, such that the radiation passes through the transparent region and is blocked by the opaque region. A shutter may be disposed between the radiation source and the mask.

10 In general, in another aspect, the present invention features a method for selectively altering a polishing pad adhesive layer. The method includes: providing a mask having a transparent region and an opaque region and directing radiation toward the mask so that the radiation is blocked by the opaque region and passes through the transparent region to impinge on the adhesive layer on the polishing pad, whereby the area of the adhesive layer corresponding to the transparent region of the mask is cured to be less adhesive.

15 Implementations of the invention may include one or more of the following features. The radiation may be ultraviolet light. The transparent region may be made of ultraviolet light transparent quartz or polymer material. The mask may be made of ultraviolet light blocking material such as paper metal, ceramic or polymer material. The transparent region may be an opening in the mask. The transparent region and the

20  
25  
30

- 5 -

opaque region may form concentric circles. The mask may have a plurality of transparent and opaque regions. The transparent regions may be circles or arc segments arranged in a pattern. The ratio of the  
5 cured region surface to the adhesive region surface may be between about 10 to 30 %. The polishing pad may be exposed to the radiation for a time varying between about 5 to 60 seconds. The radiation intensity may vary between about 100 to 1200  
10 Watts/inch.

In general, in another aspect, the invention features a method for selectively altering a polishing pad adhesive layer. The method includes: providing a  
15 polishing pad having a layer of adhesive that covers substantially an entire surface of the pad, and curing selected portions of the adhesive layer to reduce adhesive strength of the layer.

Among the advantages of the invention may be one or more of the following. By selectively altering a  
20 polishing pad adhesive layer the strength of the adhesive layer is reduced. This reduces the force applied to remove the polishing pad off the platen and the risk of injury for an operator.

Other features and advantages of the invention will  
25 be apparent from the following description of the preferred embodiments, and from the claims.

#### Brief Description of the Drawings

FIG. 1 is a perspective view of a chemical  
mechanical polishing apparatus.

30 FIG. 2 is a diagrammatic cross-sectional view of a polishing pad.

- 6 -

FIG. 3 is a flow diagram describing the method for fabricating a polishing pad with adhesive and non-adhesive regions.

5 FIG. 4 is a diagrammatic cross-sectional view of a polishing pad being exposed to ultraviolet (UV) radiation through a mask.

FIG. 4A is a diagrammatic cross-sectional view of a polishing pad having a paper mask disposed on the adhesive layer.

10 FIG. 5 is a top view of a UV mask having a "polka dot" pattern.

FIG. 6 is a top view of a UV mask having a ring pattern.

15 FIG. 7 is a top view of a UV mask having a ring and arc segment pattern.

FIG. 8 is a diagrammatic view of an apparatus for selectively removing an adhesive layer from a polishing pad.

#### Detailed Description

20 Referring to FIG. 1, a polishing apparatus 10 includes a housing 12 that contains three independently-operated polishing stations 14, a substrate transfer station 16, and a rotatable carousel 18 which choreographs the operation of four  
25 independently rotatable carrier heads 20. A more complete description of the polishing apparatus 10 may be found in U.S. Patent No 5,738,574, the entire disclosure of which is incorporated herein by reference.

30 Each polishing station 14 includes a rotatable platen 110 which supports a polishing pad 100. The



- 7 -

platen 110 is mounted to a table top 57 inside the polishing apparatus 10. In operation, a substrate 30 is loaded to the transfer station 16, from which the substrate is transferred to a carrier head 20. The carousel 18 then transfers the substrate through a series of one or more polishing stations 14 and finally returns the polished substrate to the transfer station 16. Each carrier head 20 receives and holds a substrate, and polishes it by pressing it against the polishing pad 100 on platen 110.

Referring to FIG. 2, one type of a polishing pad 100 includes a fifty mil thick hard layer 102, a fifty mil thick softer layer 104, and a pressure sensitive adhesive lower layer 106. The hard layer 102 is typically a material composed of polyurethane mixed with other fillers. The softer layer 104 is typically a material composed of compressed felt fibers leached with urethane, and adhesive layer 106 is a rubber-based or acrylic based adhesive. The hard layer 102 is adhesively bonded to the softer layer 104 by a bonding layer 107. The thickness of the polishing pad may vary between 30 to 250 mils. A polishing pad, with a hard layer composed of IC-1000, a softer layer composed of SUBA-4, and a layer composed of a rubber-based adhesive, is available from Rodel, Inc., located in Newark, Delaware (IC-1000 and SUBA-4 are product names of Rodel, Inc.). The adhesive layer 106 covers the entire bottom area of the polishing pad and has one surface 111 attached to layer 104 and a second surface 109 which is to be attached to the platen. The polishing pad is supplied with this second surface

- 8 -

109 covered with a lining 108, to prevent accidental adhesion of the pad. The lining 108 is removed before installing the polishing pad on the platen.

5 The force applied to remove the polishing pad from the platen depends upon the size of the area covered with the adhesive and the type of the adhesive. The entire bottom surface of the pad is usually covered with a continuous adhesive layer. The strength of the adhesive layer may be reduced by making selected  
10 portions of the adhesive layer less adherent. Specifically, selected areas of the adhesive layer may be partially or entirely cured to reduce their adhesive strength. For example, the selected areas of the adhesive layer may be exposed to ultra-violet (UV)  
15 light in the presence of air, as this cures the rubber-based adhesive to make it less adherent.

Referring to FIG. 3, the method 200 of producing a polishing pad with a partial adhesive layer includes providing a polishing pad with a layer of adhesive  
20 that covers the entire lower surface of the pad and removing the protective lining that covers the adhesive layer (step 202), positioning a mask with openings of a predetermined size over the adhesive layer (step 204), exposing the adhesive layer to UV  
25 light for a predetermined time (step 206), and then removing the mask and applying the pad onto the platen (step 208). After completing the polishing process the pad may be easily peeled away from the platen due to the reduced strength of the adhesive layer.

30 Referring to FIG. 4, the areas 105 of the adhesive layer 106 that are to be exposed to UV light are

- 9 -

selected by using a mask 120. The mask 120 includes windows 124 which are transparent to UV light, and opaque areas 122 which block UV light. The mask material may be paper, metal, polymer or ceramic material, or regular borosilicate glass that blocks UV light. The transparent windows may be openings formed in the mask, UV transparent suprasil type quartz, or certain types of polymer materials which are UV transparent. The areas 105 of the adhesive layer 106 that are exposed to the UV light are cured and the areas 103 that do not receive the UV light remain adhesive. In one example, the mask 120 may be a paper having openings 124 and being attached to the adhesive layer 106 (FIG. 4A). The paper mask may be covered with a lining 108.

Referring to FIG. 5, mask 120 is circular and has a diameter equal to or greater than the diameter of the polishing pad. Different patterns for the UV windows and complementing UV blocking areas are shown in FIGS 5, 6 and 7. They include transparent "polka dot" windows 124 (FIG. 5) having a diameter between 1/4 to 1/2 inch, a UV blocking ring 122 (FIG. 6) or a narrow outer ring connected to an inner circle by arc segments 122 which alternate with UV windows 124 (FIG. 7). The pattern of transparent and opaque mask areas is replicated in the cured and adhesive areas of the polishing pad, respectively.

The ratio of the surface area of the cured areas 105 to the surface of the adhesive areas 103 determines the strength of the adhesive bond between the polishing pad and the platen. The ratio of the

- 10 -

surface of the cured areas to the adhesive areas may vary between about 10% to 30%. Several cured areas, each cured area occupying a small surface, are used to prevent formation of wrinkles on the polishing pad.

5     The cured areas may be located near the center of the polishing pad to avoid large shear stresses and delamination of the polishing pad from the platen during polishing.

10     The degree of curing depends upon the exposure time and the intensity of the UV light source. Short exposure times and low UV light intensities cause partial curing, whereas long exposure times and high UV light intensities cause complete curing of the adhesive. Exposure times may vary between 5 to 60  
15     seconds, and UV power levels may vary between 100 to 600 Watts/inch. In one example a UV light of 100 Watts/inch is used and the exposure time may vary between 5 to 30 seconds for a rubber based adhesive.

20     Referring to FIG. 8, an apparatus 150 for selectively curing an adhesive layer includes a UV source 140, a mask 120 supported by a mask holder 128, a shutter 130 for blocking the UV-light to the polishing pad 100 and a support or holder 132 supporting the polishing pad. The UV source has a  
25     fast linear ramp-up and ramp-down mechanism, and variable intensity high enough to fully cover the polishing pad surface and low enough to avoid build up of heat in the pad. In one example, the UV source 140 is a UV lamp from UV Systems, Gaithersburg, Maryland  
30     having an intensity that can be linearly ramped-up to 600 Watts/inch. In other examples, a UV source having

- 11 -

a 20 inch long bulb and being rated at 1200 Watts/inch is used to irradiate a circular polishing pad along its diameter.

One embodiment of the present invention has been  
5 described. Nevertheless, it will be understood that various modifications may be made without departing from the spirit and scope of the invention.

Accordingly, other embodiments are within the scope of the following claims.

10 What is claimed is:

- 12 -

1. A polishing pad comprising:  
a first layer having a polishing surface; and  
a second layer having an adhesive region and a cured region disposed opposite the polishing surface.
- 5 2. The polishing pad of claim 1 wherein the second layer includes a plurality of adhesive and cured regions.
3. The polishing pad of claim 2 wherein the cured regions are circles.
- 10 4. The polishing pad of claim 2 wherein the cured regions are arc segments.
5. The polishing pad of claim 1 wherein the cured region and the adhesive region form concentric circles.
- 15 6. The polishing pad of claim 1 wherein a ratio of a surface area of the cured region to a surface area of the adhesive region is between about 10% to 30%.
7. The polishing pad of claim 1 further including a third layer disposed between the first and second layers.
- 20 8. The polishing pad of claim 1 wherein the cured region is partially cured.

- 13 -

9. The polishing pad of claim 1 wherein the cured region is entirely cured.

10. An apparatus for selectively altering the adhesive strength of a polishing pad adhesive layer,  
5 comprising:

a radiation source to generate radiation;  
a support for the polishing pad; and  
a mask having a transparent region and an opaque  
10 region, said mask being disposed between the radiation source and the polishing pad adhesive layer, such that the radiation passes through the transparent region and is blocked by the opaque region.

11. The apparatus of claim 10 further including a  
15 shutter disposed between the radiation source and the mask.

12. The apparatus of claim 10 wherein the transparent region is an opening.

13. The apparatus of claim 10 wherein the radiation beam is ultraviolet light.

20 14. The apparatus of claim 13 wherein the transparent region is made of a UV transparent quartz or polymer material.

15. The apparatus of claim 13 wherein the mask is made of ultraviolet light blocking material.

- 14 -

16. The apparatus of claim 15 wherein the mask is made of metal.

17. The apparatus of claim 15 wherein the mask is made of ceramic or polymer material.

5      18. The apparatus of claim 10 wherein the transparent region and the opaque region form concentric circles.

19. The apparatus of claim 10 wherein there are a plurality of transparent regions and opaque regions.

10      20. The apparatus of claim 19 wherein the transparent regions are circles.

21. The apparatus of claim 19 wherein the transparent regions are arc segments.

15      22. A method for selectively altering the adhesive strength of a polishing pad adhesive layer, comprising:

    providing a mask having a transparent region and an opaque region;

20      directing radiation toward the mask so that the radiation is blocked by the opaque region and passes through the transparent region to impinge on the adhesive layer on the polishing pad, whereby the area of the adhesive layer corresponding to the transparent region of the mask is cured to be less adhesive.



- 15 -

23. The method of claim 22 wherein the radiation is ultraviolet light.

24. The method of claim 23 wherein the transparent region is made of ultraviolet light transparent quartz  
5 or polymer material.

25. The method of claim 23 wherein the mask is made of ultraviolet light blocking material.

26. The method of claim 25 wherein the mask is made of metal.

10 27. The method of claim 25 wherein the mask is made of ceramic or polymer material.

28. The method of claim 25 wherein the mask is made of paper.

15 29. The method of claim 22 wherein the transparent region is an opening.

30. The method of claim 22 wherein the transparent region and the opaque region form concentric circles.

31. The method of claim 22 wherein there are a plurality of transparent and opaque regions.

20 32. The method of claim 31 wherein the transparent regions are circles.

- 16 -

33. The method of claim 31 wherein the transparent regions are arc segments.

34. The method of claim 22 wherein a ratio of a surface area of the cured region to a surface area of the adhesive region is between about 10% to 30%.


35. The method of claim 22 wherein the polishing pad is exposed to the radiation for a time between about 5 to 60 seconds.

36. The method of claim 23 wherein the radiation intensity is between about 100 to 1200 Watts/inch.

37. A method for selectively altering the adhesive strength of a polishing pad adhesive layer, comprising:

providing a polishing pad having a layer of adhesive that covers substantially an entire surface of the pad; and

curing selected portions of the adhesive layer to reduce adhesive strength of the layer.

**FIG. 1**




FIG 2




FIG. 3




FIG. 4




FIG. 4A




FIG. 5






FIG. 6





FIG 7



CORRECTED VERSION

(19) World Intellectual Property Organization  
International Bureau




(43) International Publication Date  
15 June 2000 (15.06.2000)

PCT

(10) International Publication Number  
**WO 00/34008 A1**

- (51) International Patent Classification<sup>7</sup>: **B24B 37/04**,  
B24D 13/14, 13/12, B29C 35/08
- (21) International Application Number: PCT/US99/28190
- (22) International Filing Date:  
29 November 1999 (29.11.1999)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
09/207,793 9 December 1998 (09.12.1998) US
- (74) Agents: BERNADICOU, Michael, A. et al.; Blakely,  
Sokoloff, Taylor & Zafman LLP, 7th floor, 12400 Wilshire  
Boulevard, Los Angeles, CA 90025 (US).
- (81) Designated States (*national*): JP, KR, SG.
- (84) Designated States (*regional*): European patent (AT, BE,  
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,  
NL, PT, SE).
- Published:  
— With international search report.
- (48) Date of publication of this corrected version:  
29 March 2001
- (15) Information about Correction:  
see PCT Gazette No. 13/2001 of 29 March 2001, Section  
II
- (71) Applicant: APPLIED MATERIALS, INC. [US/US];  
3050 Bowers Avenue, Santa Clara, CA 95052 (US).
- (72) Inventor: TOLLES, Robert, D.; 2375 Amethyst Drive,  
Santa Clara, CA 95051 (US).
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: A POLISHING PAD WITH A PARTIAL ADHESIVE COATING



(57) Abstract: A method for selectively altering a polishing pad (100) adhesive layer (106) includes providing a mask (120) having transparent regions (124) and opaque regions (122) and directing radiation toward the mask (120) so that the radiation passes through the transparent regions (124) and impinges onto the adhesive layer (106) on the polishing pad (100). The area of the adhesive layer corresponding to the transparent regions (124) of the mask (120) is cured to be less adhesive. The area of the adhesive layer corresponding to the opaque regions (122) remain adhesive.

WO 00/34008 A1

- 1 -

A POLISHING PAD WITH A PARTIAL ADHESIVE COATINGBackground

The invention relates to chemical mechanical polishing of substrates, and more particularly to a polishing pad with a partial adhesive coating, and to methods and apparatus for producing such polishing pads.

Integrated circuits are typically formed on substrates, particularly silicon wafers, by the sequential deposition of conductive, semiconductive or insulative layers. After each layer is deposited, the layer is etched to create circuitry features. As a series of layers are sequentially deposited and etched, the outer or uppermost surface of the substrate, i.e., the exposed surface of the substrate, becomes successively more non-planar. If the outer surface is non-planar, then photolithographic techniques to pattern photoresist layers might not be suitable, as a non-planar surface can prevent proper focusing of the photolithography apparatus. Therefore, there is a need to periodically planarize this substrate surface to provide a planar layer surface.

Chemical mechanical polishing is one accepted method of planarization. This planarization method typically requires that the substrate be mounted on a carrier or polishing head, with the surface of the substrate to be polished exposed. The substrate is then placed against a rotating polishing pad. In addition, the carrier head may rotate to provide additional motion

- 2 -

between the substrate and polishing surface. Further, a polishing slurry, including an abrasive and at least one chemically-reactive agent, may be spread on the polishing pad to provide an abrasive chemical solution at the interface between the pad and substrate.

A typical polishing pad includes a hard top layer and a softer bottom layer. The top layer has a high friction polishing surface, capable of transporting slurry, and a second surface adhesively bonded to a first surface of the bottom layer. A second surface of the bottom layer is typically attached to a platen by a high strength pressure-sensitive adhesive layer.

One consideration in the production of integrated circuits is process and product stability. To achieve a low defect rate, each substrate should be polished under similar conditions, i.e., same polishing surface structure. A limitation on process stability, as well as polishing throughput, is "glazing" of the polishing pad. "Glazing" occurs when the polishing pad is frictionally heated and compressed in regions where the substrate is pressed against it, as well as worn as a result of the abrasive contact. The peaks of the polishing pad are pressed and worn down and the pits of the polishing pad are filled up, so the surface of the polishing pad becomes smoother and less abrasive. As a result, the polishing time required to polish a substrate increases. Therefore, the polishing pad surface must be periodically returned to a more uniform abrasive condition, with higher friction and ability to transport slurry. This process is defined as "conditioning" and serves the purpose of

- 3 -

maintaining a high polishing rate. The conditioning process can be destructive for the polishing pad and results in reducing the lifetime of the polishing pad. Because of these reasons the polishing pad needs to be removed from the platen and replaced every 100 to 1000 substrates, depending upon the type of substrate and conditioning process.

In order to remove the pad, an operator reaches into the polishing area, grasps the polishing pad by hand or with mechanical aids and pulls it to peel it off the platen. Because of the high strength of the adhesive layer, the operator must apply a large force to pull the polishing pad off the platen. For example, the operator may need to apply pulling force of approximately 100 pounds. This large force can exceed the physical abilities of the operator and can pose a risk of injury.

#### Summary

In general, in one aspect, the invention features a polishing pad including a first layer having a polishing surface, and a second layer having an adhesive region and a cured region disposed on a surface of the first layer opposite the polishing surface.

Implementations of the invention may include one or more of the following features. The polishing pad may have a plurality of adhesive and cured regions. The cured regions may be partially or entirely cured. The cured regions may be circles or arc segments arranged in a pattern. The cured region and the adhesive region may form concentric circles. A third layer may

- 4 -

be disposed between the first and second layers opposite the polishing surface.

In general, in another aspect, the invention features an apparatus for selectively altering a polishing pad adhesive layer. The apparatus includes a radiation source generating a radiation beam, a support for the polishing pad, and a mask having a transparent region and an opaque region. The mask is disposed between the radiation source and the substrate holder, such that the radiation passes through the transparent region and is blocked by the opaque region. A shutter may be disposed between the radiation source and the mask.

In general, in another aspect, the present invention features a method for selectively altering a polishing pad adhesive layer. The method includes: providing a mask having a transparent region and an opaque region and directing radiation toward the mask so that the radiation is blocked by the opaque region and passes through the transparent region to impinge on the adhesive layer on the polishing pad, whereby the area of the adhesive layer corresponding to the transparent region of the mask is cured to be less adhesive.

Implementations of the invention may include one or more of the following features. The radiation may be ultraviolet light. The transparent region may be made of ultraviolet light transparent quartz or polymer material. The mask may be made of ultraviolet light blocking material such as paper metal, ceramic or polymer material. The transparent region may be an opening in the mask. The transparent region and the



- 5 -

opaque region may form concentric circles. The mask may have a plurality of transparent and opaque regions. The transparent regions may be circles or arc segments arranged in a pattern. The ratio of the cured region surface to the adhesive region surface may be between about 10 to 30 %. The polishing pad may be exposed to the radiation for a time varying between about 5 to 60 seconds. The radiation intensity may vary between about 100 to 1200 Watts/inch.

In general, in another aspect, the invention features a method for selectively altering a polishing pad adhesive layer. The method includes: providing a polishing pad having a layer of adhesive that covers substantially an entire surface of the pad, and curing selected portions of the adhesive layer to reduce adhesive strength of the layer.

Among the advantages of the invention may be one or more of the following. By selectively altering a polishing pad adhesive layer the strength of the adhesive layer is reduced. This reduces the force applied to remove the polishing pad off the platen and the risk of injury for an operator.

Other features and advantages of the invention will be apparent from the following description of the preferred embodiments, and from the claims.

#### Brief Description of the Drawings

FIG. 1 is a perspective view of a chemical mechanical polishing apparatus.

FIG. 2 is a diagrammatic cross-sectional view of a polishing pad.

- 6 -

FIG. 3 is a flow diagram describing the method for fabricating a polishing pad with adhesive and non-adhesive regions.

FIG. 4 is a diagrammatic cross-sectional view of a polishing pad being exposed to ultraviolet (UV) radiation through a mask.

FIG. 4A is a diagrammatic cross-sectional view of a polishing pad having a paper mask disposed on the adhesive layer.

FIG. 5 is a top view of a UV mask having a "polka dot" pattern.

FIG. 6 is a top view of a UV mask having a ring pattern.

FIG. 7 is a top view of a UV mask having a ring and arc segment pattern.

FIG. 8 is a diagrammatic view of an apparatus for selectively removing an adhesive layer from a polishing pad.

#### Detailed Description

Referring to FIG. 1, a polishing apparatus 10 includes a housing 12 that contains three independently-operated polishing stations 14, a substrate transfer station 16, and a rotatable carousel 18 which choreographs the operation of four independently rotatable carrier heads 20. A more complete description of the polishing apparatus 10 may be found in U.S. Patent No 5,738,574, the entire disclosure of which is incorporated herein by reference.

Each polishing station 14 includes a rotatable platen 110 which supports a polishing pad 100. The

- 7 -

platen 110 is mounted to a table top 57 inside the polishing apparatus 10. In operation, a substrate 30 is loaded to the transfer station 16, from which the substrate is transferred to a carrier head 20. The carousel 18 then transfers the substrate through a series of one or more polishing stations 14 and finally returns the polished substrate to the transfer station 16. Each carrier head 20 receives and holds a substrate, and polishes it by pressing it against the polishing pad 100 on platen 110.

Referring to FIG. 2, one type of a polishing pad 100 includes a fifty mil thick hard layer 102, a fifty mil thick softer layer 104, and a pressure sensitive adhesive lower layer 106. The hard layer 102 is typically a material composed of polyurethane mixed with other fillers. The softer layer 104 is typically a material composed of compressed felt fibers leached with urethane, and adhesive layer 106 is a rubber-based or acrylic based adhesive. The hard layer 102 is adhesively bonded to the softer layer 104 by a bonding layer 107. The thickness of the polishing pad may vary between 30 to 250 mils. A polishing pad, with a hard layer composed of IC-1000, a softer layer composed of SUBA-4, and a layer composed of a rubber-based adhesive, is available from Rodel, Inc., located in Newark, Delaware (IC-1000 and SUBA-4 are product names of Rodel, Inc.). The adhesive layer 106 covers the entire bottom area of the polishing pad and has one surface 111 attached to layer 104 and a second surface 109 which is to be attached to the platen. The polishing pad is supplied with this second surface

- 8 -

109 covered with a lining 108, to prevent accidental adhesion of the pad. The lining 108 is removed before installing the polishing pad on the platen.

5 The force applied to remove the polishing pad from the platen depends upon the size of the area covered with the adhesive and the type of the adhesive. The entire bottom surface of the pad is usually covered with a continuous adhesive layer. The strength of the adhesive layer may be reduced by making selected  
10 portions of the adhesive layer less adherent. Specifically, selected areas of the adhesive layer may be partially or entirely cured to reduce their adhesive strength. For example, the selected areas of the adhesive layer may be exposed to ultra-violet (UV)  
15 light in the presence of air, as this cures the rubber-based adhesive to make it less adherent.

Referring to FIG. 3, the method 200 of producing a polishing pad with a partial adhesive layer includes providing a polishing pad with a layer of adhesive  
20 that covers the entire lower surface of the pad and removing the protective lining that covers the adhesive layer (step 202), positioning a mask with openings of a predetermined size over the adhesive layer (step 204), exposing the adhesive layer to UV  
25 light for a predetermined time (step 206), and then removing the mask and applying the pad onto the platen (step 208). After completing the polishing process the pad may be easily peeled away from the platen due to the reduced strength of the adhesive layer.

30 Referring to FIG. 4, the areas 105 of the adhesive layer 106 that are to be exposed to UV light are

- 9 -

selected by using a mask 120. The mask 120 includes windows 124 which are transparent to UV light, and opaque areas 122 which block UV light. The mask material may be paper, metal, polymer or ceramic material, or regular borosilicate glass that blocks UV light. The transparent windows may be openings formed in the mask, UV transparent suprasil type quartz, or certain types of polymer materials which are UV transparent. The areas 105 of the adhesive layer 106 that are exposed to the UV light are cured and the areas 103 that do not receive the UV light remain adhesive. In one example, the mask 120 may be a paper having openings 124 and being attached to the adhesive layer 106 (FIG. 4A). The paper mask may be covered with a lining 108.

Referring to FIG. 5, mask 120 is circular and has a diameter equal to or greater than the diameter of the polishing pad. Different patterns for the UV windows and complementing UV blocking areas are shown in FIGS 5, 6 and 7. They include transparent "polka dot" windows 124 (FIG. 5) having a diameter between 1/4 to 1/2 inch, a UV blocking ring 122 (FIG. 6) or a narrow outer ring connected to an inner circle by arc segments 122 which alternate with UV windows 124 (FIG. 7). The pattern of transparent and opaque mask areas is replicated in the cured and adhesive areas of the polishing pad, respectively.

The ratio of the surface area of the cured areas 105 to the surface of the adhesive areas 103 determines the strength of the adhesive bond between the polishing pad and the platen. The ratio of the

- 10 -

surface of the cured areas to the adhesive areas may vary between about 10% to 30%. Several cured areas, each cured area occupying a small surface, are used to prevent formation of wrinkles on the polishing pad.

5       The cured areas may be located near the center of the polishing pad to avoid large shear stresses and delamination of the polishing pad from the platen during polishing.

10       The degree of curing depends upon the exposure time and the intensity of the UV light source. Short exposure times and low UV light intensities cause partial curing, whereas long exposure times and high UV light intensities cause complete curing of the adhesive. Exposure times may vary between 5 to 60  
15       seconds, and UV power levels may vary between 100 to 600 Watts/inch. In one example a UV light of 100 Watts/inch is used and the exposure time may vary between 5 to 30 seconds for a rubber based adhesive.

20       Referring to FIG. 8, an apparatus 150 for selectively curing an adhesive layer includes a UV source 140, a mask 120 supported by a mask holder 128, a shutter 130 for blocking the UV-light to the polishing pad 100 and a support or holder 132 supporting the polishing pad. The UV source has a  
25       fast linear ramp-up and ramp-down mechanism, and variable intensity high enough to fully cover the polishing pad surface and low enough to avoid build up of heat in the pad. In one example, the UV source 140 is a UV lamp from UV Systems, Gaithersburg, Maryland  
30       having an intensity that can be linearly ramped-up to 600 Watts/inch. In other examples, a UV source having

- 11 -

a 20 inch long bulb and being rated at 1200 Watts/inch is used to irradiate a circular polishing pad along its diameter.

One embodiment of the present invention has been  
5 described. Nevertheless, it will be understood that various modifications may be made without departing from the spirit and scope of the invention.

Accordingly, other embodiments are within the scope of the following claims.

10 What is claimed is:

## CLAIMS:

1. A polishing pad comprising:  
a first layer having a polishing surface; and  
a second layer having an adhesive region and a cured region disposed opposite the polishing surface.
- 5 2. The polishing pad of claim 1 wherein the second layer includes a plurality of adhesive and cured regions.
3. The polishing pad of claim 2 wherein the cured regions are circles.
- 10 4. The polishing pad of claim 2 wherein the cured regions are arc segments.
5. The polishing pad of claim 1 wherein the cured region and the adhesive region form concentric circles.
- 15 6. The polishing pad of claim 1 wherein a ratio of a surface area of the cured region to a surface area of the adhesive region is between about 10% to 30%.
7. The polishing pad of claim 1 further including a third layer disposed between the first and second  
20 layers.
8. The polishing pad of claim 1 wherein the cured region is partially cured.



- 13 -

9. The polishing pad of claim 1 wherein the cured region is entirely cured.

10. An apparatus for selectively altering the adhesive strength of a polishing pad adhesive layer,  
5 comprising:

a radiation source to generate radiation;  
a support for the polishing pad; and  
a mask having a transparent region and an opaque region, said mask being disposed between the radiation  
10 source and the polishing pad adhesive layer, such that the radiation passes through the transparent region and is blocked by the opaque region.

11. The apparatus of claim 10 further including a shutter disposed between the radiation source and the  
15 mask.

12. The apparatus of claim 10 wherein the transparent region is an opening.

13. The apparatus of claim 10 wherein the radiation beam is ultraviolet light.

20 14. The apparatus of claim 13 wherein the transparent region is made of a UV transparent quartz or polymer material.

15. The apparatus of claim 13 wherein the mask is made of ultraviolet light blocking material.

- 14 -

16. The apparatus of claim 15 wherein the mask is made of metal.

17. The apparatus of claim 15 wherein the mask is made of ceramic or polymer material.

5      18. The apparatus of claim 10 wherein the transparent region and the opaque region form concentric circles.

19. The apparatus of claim 10 wherein there are a plurality of transparent regions and opaque regions.

10      20. The apparatus of claim 19 wherein the transparent regions are circles.

21. The apparatus of claim 19 wherein the transparent regions are arc segments.

15      22. A method for selectively altering the adhesive strength of a polishing pad adhesive layer, comprising:

    providing a mask having a transparent region and an opaque region;

20      directing radiation toward the mask so that the radiation is blocked by the opaque region and passes through the transparent region to impinge on the adhesive layer on the polishing pad, whereby the area of the adhesive layer corresponding to the transparent region of the mask is cured to be less adhesive.

- 15 -

23. The method of claim 22 wherein the radiation is ultraviolet light.

24. The method of claim 23 wherein the transparent region is made of ultraviolet light transparent quartz or polymer material.

25. The method of claim 23 wherein the mask is made of ultraviolet light blocking material.

26. The method of claim 25 wherein the mask is made of metal.

27. The method of claim 25 wherein the mask is made of ceramic or polymer material.

28. The method of claim 25 wherein the mask is made of paper.

29. The method of claim 22 wherein the transparent region is an opening.

30. The method of claim 22 wherein the transparent region and the opaque region form concentric circles.

31. The method of claim 22 wherein there are a plurality of transparent and opaque regions.

32. The method of claim 31 wherein the transparent regions are circles.

- 16 -

33. The method of claim 31 wherein the transparent regions are arc segments.

34. The method of claim 22 wherein a ratio of a surface area of the cured region to a surface area of the adhesive region is between about 10% to 30%.


35. The method of claim 22 wherein the polishing pad is exposed to the radiation for a time between about 5 to 60 seconds.

36. The method of claim 23 wherein the radiation intensity is between about 100 to 1200 Watts/inch.


37. A method for selectively altering the adhesive strength of a polishing pad adhesive layer, comprising:

providing a polishing pad having a layer of adhesive that covers substantially an entire surface of the pad; and


curing selected portions of the adhesive layer to reduce adhesive strength of the layer.




2 / 4



**FIG.\_2**





**FIG.\_4**




**FIG.\_4A**

3 / 4


**FIG. 3**




**FIG. 5**



**FIG. 6**



**FIG. 7**



**FIG. 8**



# INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/28190

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B24B37/04 B24D13/14 B24D13/12 B29C35/08

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B24B B24D B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98 38042 A (WEA MFG INC) 3 September 1998 (1998-09-03) page 4, line 15 -page 7, line 8; figures	10-21
A	US 5 403 228 A (PASCH) 4 April 1995 (1995-04-04) column 4, line 37 - line 44 column 6, line 12 - line 22	1,22,37

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

19 April 2000

Date of mailing of the international search report

28/04/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040. Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Garella, M

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/28190

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9838042	A	03-09-1998	US 5932058 A	03-08-1999
			AU 6341398 A	18-09-1998
			EP 0914255 A	12-05-1999
US 5403228	A	04-04-1995	JP 6097132 A	08-04-1994